

# ONEBOND PU EXPRESS 30

## Description

OneBond PU Express 30 is a high modulus, low conductive, ultra-fast curing one-component, flexible and high-performance polyurethane adhesive for vehicle glass direct glazing. It is specifically designed to give a fast and safe drive-away time on vehicles fitted with airbags in 30 minutes.

## Technical Data

<b>Appearance</b>	Non-sag thixotropic paste
<b>Colour:</b>	Black
<b>Chemical nature:</b>	Polyurethane
<b>Curing Mechanism:</b>	Moisture-curing
<b>Curing through volume [mm] (24h - 23°C and 50% RH):</b>	ca. 3.0
<b>Hardness Shore A:</b>	ca. 60
<b>Density</b>	ca. 1.32
<b>Skin Time (min) (23°C and 50% RH):</b>	ca. 15
<b>Tensile strength [N/mm<sup>2</sup>]</b>	ca. 8.6
<b>G modulus at 10% [MPa]</b>	ca. 2.3
<b>Elongation at break [%]</b>	ca. 350
<b>Electrical volume resistivity [<math>\Omega \cdot \text{cm}</math>]</b>	$10^{10}$
<b>Application temperature (°C)</b>	From +5 to +40
<b>Temperature Resistance [°C]</b>	From -40 to +100, with brief points up to +140

## Application

Fit the bag into a manual or pneumatic air operated gun (provided with telescopic piston). The surfaces to be treated should be perfectly clean, dry and free from dust and grease. It is necessary to treat the windscreen and its bonding surface according to OneBond application guidelines, using a specific ACTIVATOR from OneBond range called PU PRIMER. It is advisable to carry out preliminary adhesion tests on the support. Specific guidance regarding the use of primers may be obtained by submitting substrate samples to our laboratories.

# ONEBOND PU EXPRESS 30

Do not cure in the presence of curing silicone sealants. Avoid contact with alcohol and other solvent cleaners during cure. When applying sealant, avoid air-entrapment. Since system is moisture-cured, permit sufficient exposure to air. Bonded elements may require additional holding or support during curing period. Tooling and finishing must be carried out within the tack-free time of the sealant.

## Areas of Application

OneBond PU Express 30 is purposely designed for bonding windscreens in the Auto Glass Replacement aftermarket, side and rear windows to passenger cars, trucks, tractors and special vehicles. Also used for bonding fiberglass reinforced plastic elements (roofs, side and frontal panels) on vehicles. It can be used in all applications where a strong elastic-structural bonding to elements of different compositions (automotive topcoat paint, metal sheets, fiberglass and reinforced plastic) is necessary and that undergo a strong mechanical or thermal stress.

## Features

- One-component polyurethane
- Solvent free, odorless
- Fast curing
- Suitable for cold and warm application
- Outstanding thixotropy, high decking and non-sagging
- High viscosity, high green strength
- High Modulus - maintains torsional rigidity and increases the vehicles NVH values
- Capable of withstanding high dynamic stresses
- Suitable for use with integral aerials
- Prevents contact corrosion in aluminum-body vehicles

## Drive Away Time (DAT)

### TÜV Crash Tested

- Drive away time: 30 minutes
- On vehicles fitted with both driver and passenger airbags

OneBond PU Express 30 is compliant to Federal Motor Vehicle Safety Standard 212 and all long-term durability requirements according to the full range of Onebond laboratory Data.

# ONEBOND PU EXPRESS 30

## Cleaning of Equipment and Personal Protective Measures

Clean the tools used with acetone or solvent. When the adhesive has not yet hardened, it can be removed using paper or a cloth. Once hardened, the product can only be removed mechanically. Avoid skin contact by using latex, rubber or polyethylene gloves. If it comes in contact with the skin, remove immediately and wash with soap and water.

## Packaging

Alu cartridge 310ml – 12 pieces per box

## Storage

OneBond PU Express 30 can be stored for 12 months in its original packaging (unopened container) between 10°C and 25°C in a cool, dry place. The storage temperature should not exceed 25°C for extended periods of time. Keep away from wet areas, direct sunlight and heat sources.

## Safety Considerations

Safety Data Sheets (SDS) are available from OneBond. SDS include information regarding the physical, health, and environmental health hazards, safety precautions, for products handling, storing and disposal. SDS are available in the language of the country or area of destination and may include locally applicable health and safety regulations. SDS are updated regularly and can be downloaded from [www.onebondadhesives.com](http://www.onebondadhesives.com). OneBond encourages users to review the up-to-date SDS before handling or using any product.

## Customer Notice

The data contained here, obtained in OneBond laboratories, are given for information only; if specifics are required, please contact OneBond Technical Department. OneBond ensures abiding quality of supplied products according to its own specifics. OneBond cannot assume responsibility for the results obtained by others which methods are not under OneBond control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. OneBond disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of OneBond products. OneBond specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.